

THERMOMASS

XPS Technical Data Sheet

Date: January 2020

Properties	Result	Unit	Standard
Compressive Strength at 10% deformation (min)	400	kg/m ³	BS EN 826
Rate of Vapour Transmission	73	µg/m ² s	ASTM E96
Max. dimensional stability of length, width and thickness	0.3	%	BS EN 1604
Max. thermal conductivity at a mean temperature of 35°C	0.026	W/mK	ASTM C518